

1560



GLOBALTM

EASIER SANDING & SUPERIOR HOLD-OUT

1560 GLOBALTM SANDING PRIMER is the latest high-build polyester primer from **Evic[®] Paint & Colour Technology**.

It sands faster and easier while providing applicators with exceptional hold-out, outstanding build per coat and, as with all GlobalTM products, impressive economy.

That's why it's not just another primer, it's GLOBALTM.

Key Product Features

- Can be thinned up to 40% for maximum economy
- Easiest sanding of all products in comparison testing
- Extra-high build polyester primer
- High solids (80%+) content
- New Part B Catalyst improves sandability and hold-out

Ideal Use

1560 Global™ Primer has been designed as part of the Global™ family of products for compatibility with all of Evic's polyurethane finishes, particularly the Global™ range of topcoats. Applications may include kitchens, vanities, commercial fitouts and other work that requires an even finish with economy and speed in mind.

Suitable for most wood substrates including MDF, melamine and wood veneers.

Available Sizes

PART A (1560A) is available in **20L** cans

PART B (1560B) is available in **0.24L** sizes

Kits (A+B) are also available

MIXING RATIO (A:B) is 100:1 (i.e. add 10mL of catalyst for every 1L of 1560 Part A)

Coverage Rate

Practical Coverage to achieve 200µm Dry Film Thickness (DFT), is **four square metres per litre.**

Mixing

For ease of incorporation, it is recommended that the solvent is mixed into Part A first, followed by Part B catalyst. Please use supplied measuring cup for Part B to ensure accuracy (too much Part B catalyst may cause the pot life to shorten dramatically, causing equipment blockage).

NOTE: There is **no danger of explosion** when mixing any combination of Part A, Part B and solvent thinner, as accelerator has been pre-added to Part A in manufacture.

Warm to Hot Conditions (25–30°C+)

1 Litre Part A + up to 400mL 765S + 10mL 1560 Part B

The 765S Solvent slows the reaction and increases pot life.

Moderate Conditions (15–25°C)

1 Litre Part A + 300–400mL 760S + 10mL 1560 Part B

The 760S Solvent slows the reaction and increases pot life.

Cool Conditions (<15°C)

1 Litre Part A + 300mL 750S + 10mL 1560 Part B

By using 750S Solvent not 760S the reaction will be more positive.

Thin Quantity

Thin up to 40% with 750S (cool), 760S (moderate) or 765S (hot) solvent, according to conditions.

Suggested Equipment

Conventional Suction Spray Guns – Anest Iwata W200 at 275kPa (40psi) or Star Pro-Series SP770 at 310kPa (45psi)

Pressure Pot – 55kPa (8psi) pot pressure with the gun pressure set to 240–275kPa (35–40psi)

Pot Life Estimates The table (overleaf) provides estimates based on 1% catalyst (100:1)

Dry Times*

Touch Dry: 1–2 hours

Time to Sand: 12–16 hours

*Based on 750S. Times apply to standard film thickness only. Overnight drying gives better results.

Recommended Film Build

1560 is a high solids, high build primer and over-application must be avoided. It is recommended that dry film build not exceed 200 µm (350 µm wet film build); inadvertent excessive build in routing and corners may reduce the coating flexibility and can cause cracking. This should be remedied by sanding back to a maximum thickness of 200 µm.

Preparation

ALUMINIUM, ZINCALUME, GALVANISED & MILD STEEL (for interior use ONLY): Use Evic 145E Etch and Protect Primer in light grey followed by **730 or 731** polyurethane primer. We do not recommend using any polyester primer over etch.

MDF BOARD: Sand edges and routes with 180 grit free-cut sandpaper or 3M Medium Sanding Sponge to remove excess raised fibre. Apply primer in 2 to 3 double wet coats allowing solvent flash off between coats.

Alternatively seal routes and edges with thinned 860 or 866 polyurethane sealer and allow to dry. Sand sealed edges and routes with 150 to 180 free-cut sandpaper or 3M Medium Sanding Sponge. Sealer will prevent fibres from resurfacing during the priming coat. Apply 2 to 3 double header wet coats, allow solvent flash off between coats. Allow overnight dry.

MELAMINE: Correctly sand with 240 to 320 grit free-cut paper and apply “top coat” directly. Alternatively, sand with 150 to 240 free-cut paper, remove all surface gloss, dust off, then apply 2 double header wet coats of primer allowing flash off between coats.

Warning: 1560 Global™ Primer does not stick to unsanded melamine. This surface must be prepared correctly especially in corners or hard to get at areas. Melamine can easily wear out paper which then effectively polishes the surface making adhesion by further coats impossible.

MELAMINE WITH RAW EDGES & ROUTES: Thin down 860 (or 866) Polyurethane Sealer 30% with 850S Solvent or thin 1560 Global™ Primer 45% with 750S–765S Solvent. Spray apply thinned sealer directly onto the raw routes and edges only, allow to dry. Sand back sealer with 150 to 180 free-cut paper or 3M Medium Sanding Sponges. Dust off then prime the sealed routes and edges only with 1560 primer, allow to dry.

Method A: Scrape excess primer and sealer off melamine surface using razor blade scrapers. Sand routes and edges with 320 to 400 free-cut paper or 3M Fine Sanding Sponges. Machine sand the melamine face with 240 to 320 free-cut paper. Ensure all oversprayed primer and sealer is removed from the melamine face.

Method B: Sand edges and routes with 320 to 400 free-cut paper or 3M Fine Sanding Sponge. Machine sand the primer off the melamine face with 240 to 320 free-cut paper making sure that all primer is removed and that there are no gloss areas left on the melamine. Dust off and wipe clean for top coating.

TIMBER: It is important to pre-seal all raw timber and veneer surfaces with either 860 (or 866) Polyurethane sealer or 850 Polyurethane clear finish before applying 1560 Global™ Primer.

SANDING: 1560 Global™ Primer should be sanded within 24 hours otherwise the primer further hardens and sanding time will increase.

Routing and Edges: (by hand) 3M Fine Sanding Sponges or 320 free-cut paper; (by machine) Festool ES125 Lightweight sander with 400 open coat paper

Face or Broad Areas: (by machine) Festool RS1C orbital sander, Festool ETS150 disk orbital or Festool Rotex eccentric disk sander with 400 or 500 free-cut paper.

Application

FINISH COAT: It is recommended that Evic’s 1600 Global finish coat be applied within 24 hours of sanding the 1560 Global™ Primer to ensure good intercoat adhesion.

Pot Life Estimates (continued)

Temperature	Solvent	Approx. Pot Life	Cure Rate
10°C	750S	2.5 hours	moderate-slow
15°C	750S	1.5 hours	moderate
	760S	4.0 hours	slow
20°C	750S	1.0 hours	fast
	760S	3.0 hours	moderate
	765S	7.0 hours	moderate-slow
25°C	750S	0.5 hours	very fast
	760S	2.0 hours	fast-moderate
	765S	5.0 hours	moderate
30°C	760S	0.5 hours	very fast
	765S	2.0 hours	fast

Note: These pot life estimates are approximate for one litre of mixed material. Catalysing larger amounts (e.g., 4L) can reduce pot life times by up to 50% (i.e. 5 hours down to 2.5 hours). As a guide, moderate cure rates give early next day sanding (16-20 hours). Using cool weather combinations in hot conditions would reduce pot life to minutes. Using hot weather combinations in cool conditions would increase pot life and cure times would become excessively slow; in extreme cases, these combinations may not cure at all.

Baking

1560 Global™ Sanding Primer responds positively to baking and dry times to sand can be reduced to as little as 1 hour. Allow 15 minutes flash off time then bake at up to 50°C for 30 minutes, allowing to cool before sanding.

Shelf Life

Part A – For safety reasons, 1560 Global™ Sanding Primer has had accelerators added during manufacture – which means the product must be used before the use-by date on the label (i.e. 4 months from manufacture). Out-of-date product will thicken and should not be used.

Part B – Store up to 6 months in cool area.

Note to Users

This is a specialised industrial coating and should only be applied by experienced and competent tradesmen and in accordance with the manufacturer's specification.

Please read Material Safety Data Sheets M1560.

More Information

Go to www.evic.com.au for product and material safety data on all Evic products. Information is also available in booklet and CD-ROM form, or by e-mail and fax transmission.

For further enquiries, call the Evic Group on (freecall) 1800 761 761.



© 2004

20 Lancaster Street, Ingleburn 2565 Australia

Phone (02) 9829 2288 Toll Free 1800 761 761 Fax (02) 9829 1612

E-mail: info@evic.com.au

www.evic.com.au